

142SP Contact adhesive

Revision: 16/07/2019

Page 1 from 2

Technical data

Basis	Polychloroprene rubber (neoprene).
Consistency	Fluid
Curing system	Physical drying and crystallisation
Density	Ca. 0,81 g/ml
Total solid content	Ca. 17 %
Viscosity (Brookfield)	250 mPa.s → 400 mPa.s
Temperature resistance**	-15 °C → 70 °C
Application temperature (text)	Ideal between +15°C and +20°C Min. +10°C, max +25°C
Evaporation time (=minimum time before bonding)	Ca. 10 min
Open time (*)	Ca. 20 min.
Pressing times	15-30s, press, roll or tap well
Drying time (23°C and 50% R.H.)	Ca. 72h
Tools	Pneumatic gun Spray opening: min. 2,5 mm Pressure: 3 - 5 bar Pressure on can: 0,5 - 2 bar
Consumption (*)	100 - 300 ml/m ² , each side

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Ready to use, toluene free, pink, sprayable contact adhesive based on polychloroprene (Neoprene®)

Properties

- Ready to use, on a sprayable viscosity
- Immediately fixed
- Fast strength build-up.
- Moisture resistant.
- Resistant against high temperatures
- Toluene free

Applications

- Used in two-sided adhesions on various materials, wood and stratified decorative coveringpanels (Formica®, Resopal®,...), veneer, stairsteps and nosings, PVC-plinths, leather, cork, textile, with each other for wood, wood derivatives, stone, concrete, plaster, metal and other smooth, non-porous surfaces.

- Meant for all adhesions where a fast bonding is required, for adhesions of two non-porous materials.
- Only for interior use

Packaging

Colour: pink
Packaging: 20L can

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C. After use, close the packaging with the original cap.

Substrates

Surface preparation: Substrates have to be clean, dry, free of dust, rust, oil and grease. The adhesive is easiest to handle in a dry environment with a temperature of minimum +15°C. Make sure both the adhesive as the substrates are acclimatized. For a better

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

142SP Contact adhesive

Revision: 16/07/2019

Page 2 from 2

adhesion it's recommended to roughen the surface with sanding paper P80, metal has to be free of rust and roughened at a St 3 level (according to ISO 8501-1). Always perform an adhesion test on non-current substrates prior to use. Both substrates have to be even and/or well matched.

Not suitable for PE, PP, PTFE (eg. Teflon®) and bituminous substrates. Given the wide variety of EPDM-substrates, a preliminary adhesion test is required.

Application method

Sprayable with the traditional spray installations or with pneumatic spray guns. Opening: 2,5 mm or wider Pressure: 3 to 5 bar Pressure on can: 0,5 to 2 bar, also sprayable with a HVLP gravity feed spray gun Remark: The adhesive doesn't spray like a paint, it forms drips and wisps. When the adhesion doesn't have to happen immediately or when bonding two non-porous materials: Apply the adhesive two-sided with the spray gun. Make sure that the adhesive is sprayed equally, the coverage has to be min. 80%. For strong porous materials (plaster, concrete, ...) a second adhesive layer has to be applied, ± 20 mins after the first layer. About 5 to 10 mins, depending on the circumstances, let dry and close within 20 minutes after applying. The bonding happens immediately. Then press hard with a roller or tap strongly with a rubber hammer. If the adhesion has to be adapted (at least 1 substrate has to be porous) or when bonding two porous materials: It's sufficient to apply 142SP Contact adhesive on one of the two sides Close immediately after usage.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Use only in well-ventilated areas. Do not smoke. In case of insufficient ventilation it is appropriate to wear respiratory protection. Consult label and material safety data sheet for more information.

Remarks

- In a colder period, the viscosity of the adhesive can raise because of the lower temperature, this will result in a more difficult adhesive to spray. If necessary, the adhesive can be diluted with max. 10% of Soudal Dissolver SP.
- When the metal is free of rust and roughened, it's important to ground the element. A discharge of static electricity can ignite the solvents if the adhesive is applied on the surface.
- Pressing the materials, during curing, is not necessary to reach the highest end strength. The initial strength and not the duration of the compression will determine the ultimate strength.
- Once the maximum open time is exceeded and the adhesive is too dry to bond, the surface can be reactivated with an extra thin layer of 142SP Contact adhesive.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.