

Fix ALL High Tack

Revision: 6/01/2022

Page 1 from 3

Technical data

| | |
|--|------------------------|
| Basis | SMX Hybrid Polymer |
| Consistency | Stable paste |
| Curing system | Moisture curing |
| Skin formation* (23°C/50% R.H.) | Ca. 5 min |
| Curing speed * (23°C/50% R.H.) | 3 mm/24h |
| Hardness** | 65 ± 5 Shore A |
| Density | 1,47 g/ml |
| Elastic recovery (ISO 7389)** | > 75 % |
| Maximum allowed distortion (ISO 11600) | ± 20 % |
| Max. tension (ISO 37)** | 3,20 N/mm ² |
| Elasticity modulus 100% (ISO 37)** | 2,30 N/mm ² |
| Elongation at break (ISO 37)** | 400 % |
| Temperature resistance** | -40 °C → 90 °C |
| Application temperature | 5 °C → 35 °C |

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Fix ALL High Tack is a high quality, neutral, elastic, 1-component adhesive sealant based on SMX-Polymer with a very high initial tack. Fix ALL High Tack is a KOMO-certified construction adhesive based on BRL3107.

- Elastic bonding of panels, profiles and other pieces on the most common substrates (wood, MDF, chipboard, etc).
- Elastic structural bonding in car and container industry.
- Joints in bathrooms and kitchens.

Properties

- High initial tack reducing the need for initial support.
- Fast curing
- Good extrudability
- high shear strength after full cure (no primer)
- Stays elastic after curing and very durable
- Impervious to mould, contains biocide with fungicidal action
- No odour.
- Can be painted with water based systems
- Good weather and UV resistance
- Does not contain isocyanates and no silicones
- Good adhesion on slightly moist substrates

Packaging

Colour: white, black, grey, alu grey, light grey, brown, beige, anthracite, oak, brick red, other colors on request

Packaging: 80 ml tube, 125 ml tube, 290 ml cartridge, 400ml foil bag, 600 ml foil bag, other packaging on request

Shelf life

15 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Chemical resistance

Good resistance to (salt)water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Applications

- Sealing and bonding in the building and construction industry.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Fix ALL High Tack

Revision: 6/01/2022

Page 2 from 3

Substrates

Substrates: all usual building substrates, treated wood, metals, PVC, plastics

Nature: rigid, clean, dry or slightly moist, free of dust and grease.

Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet).

Not suitable for PE, PP, PTFE (eg Teflon®), bituminous substrates, copper or copper-containing materials such as bronze and brass. We recommend a preliminary adhesion and compatibility test on every surface.

Joint dimensions

Min. width for bonding: 2 mm

Min. width for joints: 5 mm

Max. width for bonding: 10 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with Soudal Surface Cleaner or with Soudal Swipex, immediately after use

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Dangerous. Respect the precautions for use.

Remarks

- Fix ALL High Tack may be overpainted with water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- The drying time of alkyd resin based paints may increase.

- Fix ALL High Tack can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate, etc, may differ from manufacturer to manufacturer, we recommend preliminary compatibility test.
- While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding. For optimum adhesion the use of Surface Activator is recommended.
- Fix ALL High Tack can not be used as a glazing sealant.
- Not suitable for bonding aquariums.
- Fix ALL High Tack can be used for bonding of natural stone, but it cannot be used as a joint sealant on this type of surface. Fix ALL High Tack can therefore only be used on the bottom of natural stone tiles.
- When applying, make sure that the surface of the materials is not smudged with sealant.
- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remains will stimulate the development of fungi.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Fix ALL High Tack has a good UV resistance but can discolour under extreme conditions or after very long UV exposure.
- Discoloration due to chemicals, high temperatures, UV-radiation may occur. A change in color does not affect the technical properties of the product.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.
- Do not use in applications where continuous water immersion is possible.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Fix ALL High Tack

Revision: 6/01/2022

Page 3 from 3

Standards and certificates

- NL: KOMO certificate Nr. 33275
construction adhesive based on BRL3107.
- Australia: Watermark Level 1 certificate Nr. 23300 (details see report)
- Declaration of compliance ISEGA - Tested for use in foodstuffs-related area.

Environmental clauses

Leed regulation:

Fix ALL High Tack conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.