

Soudaflex 36FL

Revision: 24/10/2016

Page 1 from 2

Technical data

Basis	Polyurethane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 60 min
Curing speed * (20°C / 65% R.H.)	Ca. 3 mm/24h
Hardness	35 ± 5 Shore A
Density	1,30 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	± 25 %
Temperature resistance	-30 °C → 90 °C
Max. tension (DIN 53504)	Ca. 2,90 N/mm ²
Elasticity modulus 100% (DIN 53504)	0,47 N/mm ²
Elongation at break (DIN 53504)	> 900 %
Application temperature	5 °C → 35 °C

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Soudaflex 36FL is a high quality, elastic, 1-component sealant for floor joints based on polyurethane.

- Hydraulic fluids, lubricants, oils - Fuels (petrol and gasoline): Resistant to splash and spillage contact. Can withstand long-term intense contact-immersion (up to 1 week) in combination with Primer 100.

Properties

- Very easy to apply
- Good weather and UV resistance.
- Permanently elastic after curing
- Very good adhesion on many materials
- No bubble formation within sealant (in high temperature and humidity applications)
- Can be painted with most types of paint systems.

Packaging

Colour: concrete grey, other colors on request
Packaging: 600 ml sausage

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Applications

- Sealing of shrinking joints in concrete floors.
- Sealing of floor joints.
- All usual horizontal building, connection, expansion and dilatation joints.
- Excellent for sealing of joints in environments where fuel and oil contact occurs.

Substrates

Substrates: all usual building substrates, concrete, metals, ...

Nature: clean, dry, free of dust and grease. In case of cast concrete remove cement skin first.

Surface preparation: Soudaflex 36FL has a good adhesion to most substrates. In critical situations or to obtain optimum adhesion, we advice to use Primer 100 on porous surfaces. Always use Primer 100 on natural stone, no primer on non-porous substrates. No adhesion on glass, PE, PP and PTFE (Teflon). We recommend a preliminary adhesion test on every surface.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Soudaflex 36FL

Revision: 24/10/2016

Page 2 from 2

Joint dimensions*Min. width for joints:* 10 mm*Max. width for joints:* 30 mm*Min. depth for joints:* 10 mm

Recommendation sealing jobs: joint depth = 0,8 x joint width. Use closed-cell PE-backing material in order to adjust the joint depth.

Application method

Use masking tape if necessary. Apply Soudaflex 36FL evenly without air inclusions into the joint. Remove masking tape before skin formation.

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

- When painted with oxidative drying paints disturbances in the drying of the paint may occur (we recommend to do a compatibility test before application).
- Soudaflex 36FL has a good UV resistance but can discolour under extreme conditions or after very long UV exposure.

Environmental clauses*Lead regulation:*

Soudaflex 36FL conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.