



I.R.S.
Build With Quality

RUBBER
HARDWARE
TAPES
SEALANTS

1300 767 567

www.indrub.com.au

Product Data Sheet

Polyethylene

Chemically cross linked low density closed cell foam

Product	PE 30X	PE 20X	PE 15X	PE 10X
Density (ASTM D 3575)	30-40 kg/m ³	40-60 kg/m ³	60-80 kg/m ³	80-110 kg/m ³
Shore OO (ASTM D 2240)	52 - 60	63 - 70	72 - 80	80 - 88
Compression Deflection (ASTM D 3575)	at 25 % > 59 kPa	at 25 % > 75 kPa	at 25 % > 125 kPa	at 25 % > 140 kPa
Compression Set (ASTM D 3575)	25 % max	25 % max	25 % max	25 % max
Water Absorption (ASTM D 3575)	< 5 %	< 5 %	< 5 %	< 5 %
Moisture Permeability (ASTM E 96)	<0.8 gm/m ² 24 hrs @ 90% rh	<0.8 gm/m ² 24 hrs @ 90% rh	<0.8 gm/m ² 24 hrs @ 90% rh	<0.8 gm/m ² 24 hrs @ 90% rh
Elongation (ASTM D 412)	> 120 %	> 150 %	> 190 %	> 250 %
Tensile Strength (ASTM D 412)	> 0.2 Mpa	> 0.3 Mpa	> 0.4 Mpa	> 0.7 Mpa
Tear Resistance (ASTM D624)	> 1.5 Kn/m	> 2.5 Kn/m	> 5 Kn/m	> 6 Kn/m
Temperature Range	-40° C / + 80 ° C Constant + 90° intermittent	-40° C / + 80 ° C Constant + 90° intermittent	-40° C / + 80 ° C Constant + 90° intermittent	-40° C / + 80 ° C Constant + 90° intermittent
Environmental	CFC & HCFC free	CFC & HCFC free	CFC & HCFC free	CFC & HCFC free
Noise Reduction (ASTM E 336)	200 HZ : 2 odB 300 HZ : 3 odB (5mm thick foam)	N/A	N/A	N/A
Thermal Conductivity (ASTM C 51)	0.033 Kcal/MHR ² C	N/A	N/A	N/A

Flame Retardant Grades of PE conform to AS 1530-3, FMVSS302, ISO 3795, UL 94 HFI.